

Puros[®] Allograft

Dehydration of Tutoplast[®] processed human tissue before terminal gamma irradiation is part of the Tutoplast Tissue Sterilization Process. Prior to its use, proper rehydration of Puros Allograft bone products is needed to improve ductility and reduce risk of fracture for compliance with intended method of administration.¹ Following rehydration, block grafts can be manually shaped to ensure fit and rigid fixation. The following guidelines describe rehydration for Puros Allograft Particulate and Block/Dowel products. See the package leaflet shipped with each package for complete instructions for use.

Procedure for Puros Allograft Particulates

Standard Rehydration

Materials required: sterile saline solution (or Ringer's solution), instrument (e.g., spatula)

Procedure for Puros Allograft Blocks/Dowels

Vacuum Rehydration

Materials required: sterile saline solution (or Ringer's solution), syringe (size depends on graft size, min. 30 cc and 22 mm internal diameter recommended)



1. Immerse the particulates completely in sterile saline solution (or Ringer's solution).



2. Rehydration is complete when no more air bubbles escape the cancellous bone and the particulates descend to the bottom of the jar. Store the graft in the solution until ready for implantation.





- 1. Place the graft into an appropriately sized, sterile, disposable syringe. Draw sterile saline solution (or Ringer's solution) into the syringe until the graft is completely covered with the solution. Expel all of the air from the syringe.
- Thread cap onto syringe tip and apply negative pressure to the syringe by pulling on the plunger. Hold the plunger in the open position to expel any air and to rehydrate the graft. Continue this process until all air bubbles are removed. When correctly rehydrated, the graft will descend to the bottom of the syringe. Store the graft in the rehydration solution until ready for implantation.

Autologous blood or blood components may only be added after rehydration and immediately prior to the product's implantation.²

1 Thull R, Sturm A, Pesch H-J, Mechanische Eigenschaften nativer und präparierter Spongiosa, in Osteologie aktuell VII, H.-J. Pesch, H. Stoess, and B. Kummer, Editors. 1993, Spinger: Berlin. p. 157-163. ² Puros Allograft instructions for use latest revision

For more information, visit ZimVie.com

ZimVie

4555 Riverside Drive Palm Beach Gardens, FL 33410 1-800-342-5454 Phone: +1-561-776-6700 Eax: +1-561-776-1272 dentalCS@ZimVie.com



www.implacom.nl | +31 (0)577 46 1927



Unless otherwise indicated, as referenced herein, all trademarks and intellectual property rights are the property of ZimVie Inc. or an affiliate; and all products are manufactured by one or more of the dental subsidiaries of ZimVie Inc. (Biomet 3i, LLC, Zimmer Dental, Inc., etc.) and marketed and distributed by ZimVie Dental and its authorized marketing partners. Puros Allografts are processed by RTI Surgical, Inc. Some Puros Allografts are processed by Tutogen Medical GmbH. Tutoplast is a registered trademark of Tutogen Medical GmbH. For additional product information, please refer to the individual product labeling or instructions for use. Product clearance and availability may be limited to certain countries/regions. This material is intended for clinicians only and does not comprise medical advice or recommendations. Distribution to any other recipient is prohibited. This material may not be copied or reprinted without the express written consent of ZimVie. ZV1767 REV A 10/23 ©2023 ZimVie. All rights reserved.

